

2007 Florida Drilling Intercepts

<u>Hole</u>	<u>Interval (meters)</u>	<u>Thickness (m)</u>	<u>Pb (%)</u>	<u>Zn (%)</u>	<u>Pb+Zn</u>	<u>Ag (g/t)</u>
V-28	93.25 to 93.95	0.70	2.34	12.37	14.71	31.21
	182.15 to 182.45	0.30	9.49	17.50	26.99	101.00
V-26	153.65 to 154.1	0.45	1.00	2.44	3.44	3.30
V-09	No Intercepts					
V-18	91 to 93.9	2.90	1.04	7.05	8.09	15.96
	177.25 to 177.65	0.40	0.01	15.30	15.31	4.30
V-19	167.35 to 168.35	1.00	0.00	4.48	4.48	5.30
	281.7 to 282.7	1.00	1.31	0.78	2.09	11.10
V-10	416.36 to 419.8	3.44	0.42	7.42	7.84	3.92
	442.5 to 443.5	1.00	5.97	29.50	35.47	36.70
V-20	217.85 to 218.5	0.65	0.02	14.68	14.70	22.72
V-21	187 to 187.85	0.85	0.42	2.25	2.67	2.90
	190 to 192	2.00	0.95	1.33	2.28	4.75
	262.8 to 354.75	91.95	1.74	5.50	7.24	12.61
	including 262.8 to 264	1.20	0.83	10.90	11.73	27.60
	including 270.3 to 271	0.70	0.85	10.40	11.25	3.70
	including 285.9 to 287.9	2.00	3.22	19.60	22.82	26.85
	including 307.2 to 309.9	2.70	8.90	12.38	21.28	38.41
	including 319.2 to 329.4	10.20	7.04	16.93	23.97	51.48
	including 334.8 to 338.8	4.00	0.58	5.54	6.12	11.00
	including 343.75 to 354.75	11.00	4.02	15.38	19.40	29.45
V-21A	258.45 to 258.75	0.30	1.28	5.18	6.46	4.80
	261.45 to 262.45	1.00	0.49	6.82	7.31	21.30
V-10A	no intercepts					
V-40	11.4 to 12.7	1.30	0.04	2.23	2.27	2.80
	22.1 to 28.1	6.00	5.38	23.65	29.04	36.75
	40.4 to 41.7	1.30	2.34	11.35	13.69	12.00
	55.3 to 57.3	2.00	0.00	12.17	12.18	19.11
	including 55.6 to 56.3	0.70	0.01	32.83	32.84	50.40
V-41	69.9 to 71.9	2.00	0.07	6.05	6.12	1.68
	106.5 to 109.5	3.00	0.00	4.01	4.01	3.13
	112.2 to 125	12.80	0.14	6.58	6.72	10.15
	137.8 to 140.8	3.00	0.67	2.27	2.94	3.47

V-43	85.4 to 90.7	5.30	0.18	10.41	10.59	3.58
V-35	274.05 to 275.05	1.00	1.69	4.32	6.01	8.90
V-34	235 to 236	1.00	0.08	5.33	5.41	1.40
V-42	118.8 to 119.8	1.00	0.20	2.70	2.90	24.50
V-08	335.3 to 335.6	0.30	7.66	0.44	8.10	17.90
V-33	214.4 to 227.3	12.90	0.73	5.44	6.17	9.71
including	214.4 to 220	5.60	0.60	5.75	6.35	8.04
and	224.3 to 227.3	3.00	2.02	12.64	14.66	26.47
	244.7 to 247.7	3.00	0.97	9.57	10.54	11.87
V-38	56.25 to 56.75	0.50	11.15	0.46	11.61	45.70
	84.05 to 90.35	6.30	0.51	3.80	4.31	3.45
V-39	91.8 to 92.3	0.50	5.83	23.00	28.83	48.30
V-39-A	72 to 73	1.00	2.36	1.89	4.25	11.60
	84 to 90.6	6.60	1.77	12.61	14.38	15.70
including	84 to 87	3.00	3.61	24.63	28.24	31.13
and	90.3 to 90.6	0.30	1.97	26.40	28.37	23.30
V-08B	308.55 to 309.55	1.00	6.20	9.65	15.85	36.30
V-32	307.60 to 308.10	0.50	1.75	29.55	31.30	100.00
V-36	82.55 to 84.55	2.00	0.06	6.53	6.59	1.24
	94.55 to 96.55	2.00	7.58	15.53	23.11	99.60
	134.45 to 134.75	0.30	3.68	26.10	29.78	43.50
	287.55 to 288.05	0.50	6.13	9.57	15.70	45.10
V-35A	270.6 to 272.6	2.00	0.15	18.73	18.88	3.34
	287.55 to 288.05	0.50	6.13	9.57	15.70	45.10
	335.15 to 336.15	1.00	0.82	2.84	3.66	13.70
V-23	407.5 to 410.8	3.30	0.21	1.31	1.53	1.58
including	407.5 to 407.8	0.30	0.06	5.51	5.57	1.90
including	410.5 to 410.8	0.30	1.60	8.12	9.72	1.60
and	425.4 to 425.7	0.30	0.15	4.18		1.80